

TECHNICAL DATA SHEET


CLEARCOAT AT-100 PLUS

The identification code: A-LBP
Line: AT-100


PRODUCT DESCRIPTION

Clearcoat in Medium Solid system is characterized by good hardness and resistance to UV rays. It is resistant to troublesome weather conditions. It has very good resistance to stone impact, coating does not chip off even with strong strokes of stones. Durability and excellent gloss gives the coating the "colour depth" effect and guarantees its high quality. Is compatible with all solvent basecoats and water basecoats. Occurs with hardener in slow, standard or rapid version.

MIXING RATIO

	A: Clearcoat AT-100 PLUS [code: A-LBP]	100
	B: Hardener AT-100 PLUS [code: A-UP]	50
	C: Acryl thinner AT-100 [code: A-RA]	4 - 6%
Comments:	Amount of thinner calculated for weight of the clearcoat.	
	Do not use other thinner than acryl thinner AT-100.	

APPLICATION



	Number of layers	2
	Pressure	2 - 2,5 bar
	Nozzle	1.3 - 1.4 mm
	Flash off between layers	10 - 12 min
	Mixture life after mixing clearcoat with standard type of hardener	60 min at 20°C

The first layer of clearcoat is applied to the pre-dried layer of basecoat. Second layer of clearcoat should be applied as a full layer and left to complete flow and hardening. Coating of clearcoat can be hardened by using IR heater. Please note that IR heater should not be turned on earlier than after about 15 minutes after application last layer of clearcoat. When painting large surfaces it is recommended to use a hardener and the acryl thinner - slow version.

TECHNICAL DATA SHEET CLEARCOAT AT-100 PLUS

The identification code: A-LBP
Line: AT-100

ADDITIONAL INFORMATION

	Viscosity (DIN 4/20°C)	
	Without thinner	17 - 18 s
	After adding thinner	16 - 17 s
	Operating hardness	14 h at 20°C
		45 min at 50°C
	Ending hardness	4 days
	Dust-free	20 min at 20°C
		3 min at 50°C

CONTENT OF VOLATILE ORGANIC COMPOUNDS

Maximum content of VOC in product	545 g/l
VOC for category: II,B/e	840 g/l

Clearcoat complies standards of EU Directive 2004/42/CE/II,B/e(840)

GLOSS

Output gloss	96°
--------------	-----

STORAGE TIME AND CONDITIONS

Store in tightly closed containers, in a cool, dry place away from sources of fire and heat. Avoid exposure to sunlight. Expiration date: 12 months from date of manufacture - date on the top of container.

CLEANING EQUIPMENT

For cleaning equipment can be used acryl thinner [code: E-RA] or nitro thinner [code: E-RN]. It is recommended to use thinner for cleaning paint spray guns EXLAK [code: E-RDMP].

HEALTH AND SAFETY REGULATIONS

See Safety Data Sheet of the product.

SPECIFIC WEIGHT

About 1.0 g/cm³