

TECHNICAL DATA SHEET


CLEARCOAT OPTIMAL

Line: ECONOMY



PRODUCT DESCRIPTION

Clearcoat in Medium Solid system with high density for thinning and high amount of solids. Clearcoat has good levelling and very easy application properties. It has good gloss and good resistance to UV rays and weather conditions. Can be easily polished.

MIXING RATIO

	A: Clearcoat Optimal	100
	B: Hardener Optimal	50
	C: Acryl thinner EXLAK	8 - 9% of volume of clearcoat
		5 - 6% of volume of mixture clearcoat with hardener
Comments:	Do not use other thinner than acrylic thinner EXLAK.	

APPLICATION

	Number of layers	2
	Pressure	2 - 2,5 bar
	Nozzle	1.3 - 1.4 mm
	Flash off between layers	10 - 12 min
	Mixture life after mixing clearcoat with standard type of hardener	60 min at 20°C


The first layer of clearcoat is applied to the pre-dried layer of basecoat. Second layer of clearcoat should be applied as a full layer and left to complete flow and hardening. Coating of clearcoat can be hardened by using IR heater. Please note that IR heater should not be turned on earlier than after about 15 minutes after application last layer of clearcoat. When painting large surfaces it is recommended to use a hardener and the acryl thinner - slow version.

TECHNICAL DATA SHEET

CLEARCOAT OPTIMAL

Line: ECONOMY

ADDITIONAL INFORMATION

	Viscosity (DIN 4/22°C)	
	Without thinner	18 - 19 s
	After adding thinner	17 - 18 s
	Operating hardness	14 h at 20°C
		45 min at 50°C
	Ending hardness	4 days
	Dust-free	25 min at 20°C
		10 min at 50°C

CONTENT OF VOLATILE ORGANIC COMPOUNDS

Maximum content of VOC in product	590 g/l
VOC for category: II, B/e	840 g/l

Clearcoat complies standards of EU Directive 2004/42/CE/II, B/e(840)

GLOSS

Output gloss	96°
--------------	-----

STORAGE TIME AND CONDITIONS

Store in tightly closed containers, in a cool, dry place away from sources of fire and heat. Avoid exposure to sunlight. Expiration date: 12 months from date of manufacture - date on the top of container.

CLEANING EQUIPMENT

For cleaning equipment can be used acryl thinner [code: E-RA] or nitro thinner [code: E-RN]. It is recommended to use thinner for cleaning paint spray guns EXLAK [code: E-RDMP].

HEALTH AND SAFETY REGULATIONS

See Safety Data Sheet of the product.

SPECIFIC WEIGHT

About 1.0 g/cm³